

# LH 380 Liebherr (International)

## Standards

Liebherr

## Chemical composition

**C** < 0.2

**Si** < 0.55

**Mn** < 1.7

**Fe** Rest

The basic chemical composition

## Properties

Typical characteristics

**Yield Strength: > 380 MPa**

**Tensile Strength: 500 - 640 MPa**

Calculated properties

**Density: 7.84 g/cm<sup>3</sup>**

## Additional information

Structural steel